



Epoxy.com Product #1

100% Solids Hi-Build Epoxy Coating

GENERAL DESCRIPTION

Product #1 a two component, 100% solids epoxy Hi-Build epoxy coating used for high foot traffic and light to moderate forklift traffic areas where abrasion resistance is required; for protection against mild corrosion and as a decorative waterproof coating for walls, floors, tanks, etc. It can be broadcast with appropriate silica sand (contact Epoxy.com Technical Support for a recommendation), to create a thicker flooring system in high abrasion situations.

ADVANTAGES

Moisture Insensitive
Ceramic like finish
Sprayable
Solvent Free
Waterproof
Extremely Durable
Chemical Resistant

SURFACE PREPARATION

Surface must be clean and sound. Remove all dirt, laitance, grease curing compounds and other foreign matter by sandblasting, or mechanical abrasion. Remove water and dust from all surfaces with an oil free blast immediately prior to application. See Epoxy.com Surface Preparation Guide for more details.

MIXING INSTRUCTIONS

Temperature of Epoxy.com Product #1 must be 50 degrees F or above at time of mixing. Stir each component separately before blending. Mix two parts by volume of Part A with one part by volume of Part B for three minutes with a low speed electric drill motor equipped with a mixing paddle.

APPLICATION

Over Concrete surfaces Epoxy.com Product #899 Primer is recommended. Then apply Product #1 with a roller, brush, or spray equipment. Two coats are recommended. Thickness per coat should be 7-10 mils. Seven days cure time is required to reach maximum chemical resistance. For more information before installing please see installation tips at <https://www.epoxy.com/install.htm>.

LIMITATIONS

DO NOT apply at temperatures below 40 degrees F. Surface must be dry.

SAFETY PRECAUTIONS

Prolonged or repeated exposure may cause eye and skin irritation. If contact occurs, wash immediately and seek medical help. Use safety glasses with side shields and wear protective rubber gloves.

CLEANING

All tools and equipment should be cleaned before the system gels. Use MEK, Acetone, or any lacquer solvent

| APPLICATION PROPERTIES @77 DEGREES F | |
|--|---------------------------------|
| Mix Ratio | 2:1 By Volume |
| Viscosity (mixed) | 950 CPS |
| Pot Life (200 gr.) in minutes @70 Degrees F. | 30-40 (normal cure) |
| Set Time in Hours @ 70 Degrees F. | 10-12 (normal cure) |
| Initial Cure | 24 Hours |
| Final Cure | 5 Days |
| Packaging Unit Size | 3 gal. 15 gal. |
| Standard Colors | See Color Chart |
| Typical Coefficient of Friction-Rubber Shoe Surface with Epoxy.com Product # 50 Anti-skid Fine Non-Skid Added | ASTM F-489 |
| Static Friction w/ Saltwater Solutions on surface | 0.90-0.97 |
| Static Friction w/ oil on Surface | 0.72-0.75 |
| Sliding Friction w/ Saltwater Solution on Surface | 0.87-.090 |

**FOR INDUSTRIAL USE ONLY
KEEP AWAY FROM CHILDREN**

For more information please contact:

Epoxy.com
352-489-1666 (Phone)
352-465-3497 (Fax)
info@epoxy.com
www.epoxy.com

This information is presented in good faith to assist in determining whether this product is suitable for application. No warranty or representation, however, is intended or made, nor is protection from any law or patent to be inferred, and all patent rights reserved. Epoxy.com a division of Epoxy Systems, Inc. warrants its products (when properly stored) for the period of time as follows: Epoxies, Product #315, Product #315BC, and Product #316 one (1) year; Polyesters, Methyl Methacrylates (normal) two (2) months and Polyurethanes Four (4) months; Power Tools and Equipment 90 days; Vinyl Esters, High Molecular Weight Methacrylates (HMMA) and all other resins (not specifically mentioned above) 30 days; hand tools (non-power tools) 30 days. Epoxy.com warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Epoxy.com. If any product fails to meet this warranty, the liability of Epoxy.com will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Epoxy.com within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). Epoxy.com may in its discretion refund the price received by Epoxy.com in lieu of replacing the material. No customer, distributor, or representative of Epoxy.com is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Epoxy.com. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Epoxy.com reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. Epoxy.com'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND Epoxy.com SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. All quotes and sales subject to availability.