



Epoxy.com Product #12

Chemical Resistant Epoxy Primer

GENERAL DESCRIPTION

Epoxy.com Product #12 is a two component; seamless 100% solids epoxy primer system with High Chemical Resistance and High Bond Strength. The epoxy may be applied as a primer for most High End Industrial coatings, like Epoxies, MMA, Polyurethane's, Vinyl Esters, Polyesters, etc.

APPLICATIONS

Can be used as a primer to any of the materials listed above, being installed in, but not limited to the following areas:

Aisle Ways	Machine Shops
Assembly Plants	Manufacturing Areas
Bakeries	Marine Surfaces
Basement Floors	Meat Preparation Areas
Bottling Plants	Mortuaries
Break Rooms	Nuclear Plant Floors
Cafeterias	Offices
Canning Plants	Patching concrete
Car Washes	Photography Processing Areas
Cells	Power Plants
Chemical Storage Areas	Printing Plants
Chemical Processing Areas	Produce Preparation Areas
Church Floors	Pool Decks
Classroom Floors	Ramps
Corridors	Research Facilities
Educational Facilities	Rest Rooms
Entrances	Restaurants
Food Plants	Semiconductor Plants
Fork Lift Areas	Sewer Plants
Health Care Facilities	Shop Floors
Hospitals	Shopping Centers
Kennels	Shower Rooms
Kitchens	Store Floors
Laboratories	Show Rooms
Law Enforcement Facilities	Supermarkets
Laundries	Veterinary Facilities
Leveling concrete	Water Plants Warehouses
Loading docks	& many others
Locker Rooms	

ADVANTAGES

LOW ODOR
STRONG YET RESILIENT
HIGH BOND STRENGTH
ABRASION RESISTANT
CHEMICAL RESISTANT

SURFACE PREPARATION

Surface must be clean and sound. Remove all dirt, laitance, grease curing compounds and other foreign matter by sandblasting, mechanical abrasion. If acid etching is used follow with abrasive or mechanical abrasion. Remove water and dust from all surfaces with an oil free blast, or vacuum, immediately prior to application.

MIXING INSTRUCTIONS

Temperature of Product #12 must be 65 degrees F or above at time of mixing. Stir each component separately before blending. Mix two parts by volume of Part A with one part by volume of Part B for three minutes with a low speed electric drill motor equipped with a mixing paddle.

APPLICATION

Epoxy.com Product #12 can be applied with brush, roller, trowel, airless sprayer or squeegee. Apply a coat of Product #12 to surface to be finished. Average application rate is 200 square feet per gallon on smooth concrete. Contact Epoxy.com For information on how to adjust application rate to account for a substrate that is more porous, or has more texture.

If anti-skid is required, or to improve trowelability of the next coat, it may be broadcast with aggregate (while epoxy is still wet). This can be done by hand or mechanical means. Allow them to dry. Then sweep off excess aggregate. Sand surface (if required) to desired texture. It may be left a final sealer or you may install other high end top-coats over the Product #12 at a rate as recommended by that material.

LIMITATIONS

New concrete should be at least 28 days old. Temperature of substrate must be above 55 degrees F. DO NOT thin. For outdoor use contact Epoxy.com for technical assistance.

SAFETY PRECAUTIONS

Prolonged or repeated exposure may cause eye and skin irritation. If contact occurs, wash immediately and seek medical help. Use safety glasses with side shields and wear protective rubber gloves.

CLEANING

All tools and equipment should be cleaned before the system gels. Use MEK, Acetone, or any lacquer solvent.

APPLICATION PROPERTIES @77 DEGREES F	
Mix Ratio	2:1 By Volume
Viscosity (mixed)	<500 CPS
Pot Life (200 gr.)	30 minutes
Recoat Time	6-10 hours depending on temperature
Maximum Time to Recoat	24-48 hours depending on temperature
Final Cure	7 Days
Packaging (unit size)	gallons, pails, drums
PHYSICAL PROPERTIES (neat)	
Bond Strength (ASTM C-882)	2100 p.s.i
Flexural Strength (ASTM D-2240)	>6000 p.s.i (7 days)
Compressive Strength (ASTM D-695)	>9900 p.s.i (7 days)
Absorption (ASTM D-570)	<1%
Thermal Shock	40 Hr. @ 10 Degrees F., 3 Min. @ 212 Degrees F. shock water 33 Degrees F.

**FOR INDUSTRIAL USE ONLY
KEEP AWAY FROM CHILDREN**

For more information please contact:

Epoxy.com.

352-489-1666 (Phone)

352-465-3497 (Fax)

info@epoxy.com

www.epoxy.com

Epoxy.com a division of Epoxy Systems, Inc. warrants its products (when properly stored) for the period of time as follows: Epoxies, Product #315, Product #315BC, and Product #316 one (1) year; Polyesters, Methyl Methacrylates (normal) two (2) months and Polyurethanes Four (4) months; Power Tools and Equipment 90 days; Vinyl Esters, High Molecular Weight Methacrylates (HMMA) and all other resins (not specifically mentioned above) 30 days; hand tools (non-power tools) 30 days. Epoxy.com warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Epoxy.com. If any product fails to meet this warranty, the liability of Epoxy.com will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Epoxy.com within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). Epoxy.com may in its discretion refund the price received by Epoxy.com in lieu of replacing the material. No customer, distributor, or representative of Epoxy.com is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Epoxy.com. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Epoxy.com reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. Epoxy.com 'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND Epoxy.com SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. All quotes and sales subject to availability.