



Epoxy.com Product #206

Cold Temperature Cure Polymeric Mortar

DESCRIPTION

Epoxy.com Product #206 Cold Temperature Cure POLYMERIC MORTAR RESIN is a specially formulated binder for cold temperature applications. Able to cure at temperatures as low as 35°F. They are often used in coolers and food preparation areas that require constant low temperatures. Product #206 Cold Temperature Cure POLYMERIC MORTAR is also frequently used in room temperature applications to meet super-fast cure, limited shutdown needs.

ADVANTAGES

- Low temperature cure
- Low odor during application and cure--will not taint foods
- Superior stain and chemical resistance
- Bonds well to cool, damp substrates

CONSIDERATIONS

- Substrate temperature must be a minimum of 35°F
- Substrate must be free of dirt, waxes, curing agents, and other foreign materials

COMPOSITION

100% Solids Polymeric Resin, Polymeric Hardeners and Fillers

APPLICATION

SURFACE PREPARATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared. For more information, Contact Epoxy.com Technical Service Department.

INSTALLATION

Installation of Epoxy.com Product #206 Cold Temperature Cure Polymeric Mortar Resin varies with your application needs. Contact Epoxy.com Technical Support Department for more details.

CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with xylene or lacquer thinner.

COVERAGE

Epoxy.com Product #206 Cold Temperature Cure BINDER coverage varies with application method. Contact Epoxy.com Technical Support Department for estimating support.

COLOR SELECTION

Light Grey, Sand, Old Gold, Mocha, Brick Red, Taupe, Dark Grey, Slate Blue, Colonial Green, Charcoal, Caramel, Gem Grey, White Sand, White, and Black. Safety Yellow, Deep Blue, Ivy, and Honey Clear. Custom colors available at an additional charge.

TECHNICAL DATA

Viscosity @ 75°F	1,000 cps
Mixing Ratio	2 Parts A to 1 Part B by Volume
Solids Content	100%, by volume
Volatile Organic Content (VOC)	0
Weight per gallon	10.0-11.5 pounds per gallon, mixed

CURE/DRY TIME

Pot Life	15 minutes @ 75°F
Dry to Touch	2-3 hours @ 75°F; 14-16 hours @ 35°F
Re-Coat	3-4 hours @ 75°F; 14-16 hours @ 35°F
Light Traffic	5-6 hours @ 75°F; 24 hours @ 35°F
Full Cure & Maximum Resistance	5 days

FOR INDUSTRIAL USE ONLY KEEP AWAY FROM CHILDREN

For more information please contact:

Epoxy.com.

352-489-1666 (Phone)

352-465-3497 (Fax)

info@epoxy.com

www.epoxy.com

Epoxy.com a division of Epoxy Systems, Inc. warrants its products (when properly stored) for the period of time as follows: Epoxies, Product #315, Product #315BC, and Product #316 one (1) year; Polyesters, Methyl Methacrylates (normal) two (2) months and Polyurethanes Four (4) months; Power Tools and Equipment 90 days; Vinyl Esters, High Molecular Weight Methacrylates (HMMA) and all other resins (not specifically mentioned above) 30 days; hand tools (non-power tools) 30 days. Epoxy.com warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Epoxy.com. If any product fails to meet this warranty, the liability of Epoxy.com will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Epoxy.com within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). Epoxy.com may in its discretion refund the price received by Epoxy.com in lieu of replacing the material. No customer, distributor, or representative of Epoxy.com is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Epoxy.com. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Epoxy.com reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. Epoxy.com'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND Epoxy.com SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. All quotes and sales subject to availability.

Many of our products are made on an individual order basis. Unless authorized in writing by Epoxy.com a division of Epoxy Systems, Inc. in writing before the material is made, there are no returns on items purchased from us, once the order has been processed, and the material made. In the event of authorized returns a restocking charge will be charged in the amount of 30% of the value of the material returned or \$150 whichever is greater. No returns on non-list priced items. All Returns are for merchandise (store) credit only, no cash or credit card credits. In the event of a return, buyer is responsible for the cost of shipping and handling in both directions.