



Epoxy.com Product #32

100% Solids Flexible Epoxy Membrane & Mortar

GENERAL DESCRIPTION

Epoxy.com Product #32 Flexible Epoxy is a flexible resin used as an epoxy membrane and as a flexible epoxy mortar. Epoxy.com Product #32 Flexible Epoxy is a two component, 100% solids epoxy used as a base in many Epoxy.com Flexible Epoxy Floor and Mortar Systems. Flexible Epoxy resists cracking caused by horizontal substrate movement, providing a crack resistant, resilient, sound absorbent, waterproof, durable floor.

Epoxy.com Product #32 Flexible Epoxy offers stress-relieving properties for floor slabs that show movement or vibration. Product #32 Flexible Epoxy is excellent for use in areas such as mechanical equipment rooms, large animal rooms and activity centers.

ADVANTAGES

Crack Resistant - Elasticity Allows Substrate Movement

Ultimate Elongation of 100%

Moisture Insensitive

Reduces Noise Created by Mechanical Vibrations

Waterproof

Good Shock Absorption Qualities

Good Chemical Resistance

SURFACE PREPARATION

Surface must be clean and sound. Remove all dirt, laitance, grease curing compounds and other foreign matter by sandblasting, shot blasting, or mechanical abrasion. Remove water and dust from all surfaces with an oil-free blast immediately prior to application.

MIXING AND INSTALLATION INSTRUCTIONS

Application of Epoxy.com Product #32 Flexible Epoxy can be applied with brush roller or spray. When spraying back-roll to ensure good contact with surface. Two coats at a minimum thickness of 20 mils each (80 square feet per gallon) is recommended. Do not use in temperatures below 50 degrees F, as cooler temperatures delay hardening.

SAFETY PRECAUTIONS

Prolonged or repeated exposure may cause eye and skin irritation. If contact occurs, wash immediately and seek medical help. Use safety glasses with side shields and wear protective rubber gloves.

CLEANING

All tools and equipment should be cleaned before the system gels. Use MEK, Acetone, or any lacquer solvent.

APPLICATION PROPERTIES @77 DEGREES F	
Mix Ratio	1:1 by volume
Gel Time	40 minutes
Color	Gray, Clear
Viscosity (mixed)	2,200 CPS
Initial Cure	8 hours
Final Cure	48-72 hours
PHYSICAL AND PERFORMANCE PROPERTIES	
Tensile Strength (ASTM D-412)	1000 p.s.i
Ultimate Elongation (ASTM D-412)	100%
Adhesion (unprimed - ASTM D-904)	30 pli
Adhesion to Concrete (ACI Committee 403)	250 p.s.i (Concrete Fails)
Hardness Shore A (ASTM D-2240)	70-80
Impact Resistance (ASTM D-2794)	16 ft. lbs

**FOR INDUSTRIAL USE ONLY
KEEP AWAY FROM CHILDREN**

For more information please contact:

Epoxy.com.
352-489-1666 (Phone)
352-465-3497 (Fax)
info@epoxy.com
www.epoxy.com

Epoxy.com a division of Epoxy Systems, Inc. warrants its products (when properly stored) for the period of time as follows: Epoxies, Product #315, Product #315BC, and Product #316 one (1) year; Polyesters, Methyl Methacrylates (normal) two (2) months and Polyurethanes Four (4) months; Power Tools and Equipment 90 days; Vinyl Esters, High Molecular Weight Methacrylates (HMMA) and all other resins (not specifically mentioned above) 30 days; hand tools (non-power tools) 30 days. Epoxy.com warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Epoxy.com. If any product fails to meet this warranty, the liability of Epoxy.com will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Epoxy.com within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). Epoxy.com may in its discretion refund the price received by Epoxy.com in lieu of replacing the material. No customer, distributor, or representative of Epoxy.com is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Epoxy.com. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Epoxy.com reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. Epoxy.com'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND Epoxy.com SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. All quotes and sales subject to availability.