



Epoxy.com Product #402

Two Component Chemical Resistant Polyurethane Coating

GENERAL DESCRIPTION

Epoxy.com PRODUCT #402 is a two component chemical resistant polyurethane coating. The high gloss finish offers excellent abrasion resistance, chemical and stain resistance, and color retention.

Epoxy.com PRODUCT #402 can be used equally well on vertical or horizontal surfaces. It is ideal for concrete floors and walls in warehouses, storage facilities, aircraft hangers, animal housing, and vehicle maintenance facilities.

This Product is not for use in California

ADVANTAGES

- ✦ Excellent Abrasion Resistance
- ✦ Excellent Chemical Resistance
- ✦ Exterior and Interior Uses
- ✦ May be used on both Horizontal and Vertical Applications

SURFACE PREPARATION

Surface must be clean and sound. Remove all dirt, laitance, grease curing compounds and other foreign matter by sandblasting, or mechanical abrasion. Remove water and dust from all surfaces with an oil-free blast immediately prior to application.

APPLICATION

Prime: For best bond to properly prepared surface, use Epoxy.com Product #899 Primer.

Body: Apply **Epoxy.com PRODUCT #402** with brush, roller (short napped), or squeegee followed with back rolling to get recommended thickness (3 mils DFT).

Finish: Apply top coat as required (minimum 3 mils DFT).

Epoxy.com PRODUCT #402 is also available in the following forms:

As a slip or skid resistant finish using a non-skid additive in the finish.

LIMITATIONS

Surface must be dry. Minimum application temperature of 40°F (Contact Epoxy.com Technical Support for Low Temperature Cure). Maximum application temperature of 100°F. Avoid applications on surfaces without effective vapor barriers.

SAFETY PRECAUTIONS

Prolonged or repeated exposure may cause eye and skin irritation. If contact occurs, wash immediately and seek medical help. Use safety glasses with side shields and wear protective rubber gloves.

CLEANING

All tools and equipment should be cleaned before the system gels. Use MEK, Acetone, or any lacquer solvent.

Physical Properties	
Color	Standard colors for this product are: Clear (satin and gloss), White #001, Light Gray #100, White Sand #210, Taupe #300, Mocha #400, Caramel #420, & Brick Red #900.
Gloss, 60 ⁰ F	85-100
Mix Ratio	2Ato 1B by volume
Pot Life	30-40 minutes @ 70 ⁰ F
VOC	405 gm/liter
Solids Content, % vol	56.0
Coverage	300 ft ² /gal @ 3 mils DFT
DRY TIME	
10-20 mil film	10~14 hrs
Light Traffic	16 hrs
Ultimate Cure @ 74⁰F	5 days
@50⁰F	14days

PERFORMANCE PROPERTIES	
Adhesion to concrete ACI Committee 403	200 p.s.i (concrete fails)
Abrasion Resistance ASTM-C501	30-40 mg loss (CS-17 wheel, 1 kg load, 1000 cycles)
Service Temperature MIL- D-3134F	160 ⁰ F (immersion) 250 ⁰ F (dry heat)
Impact Resistance MTI-D-3134F ss 4.7.5	Withstands 16ft./lbs. no cracking, delamination or chipping
Elevated Temperature Resistance MIL-D-3134F ss 4.7.3	No slip or flow at required temperatures at 158 ⁰ F
Water Absorption (24. hr. immersion) ASTM-D-670-63	0.10% maximum

Standard colors for this product are: White #001, Light Gray #100, White Sand #210, Taupe #300, Mocha #400, Caramel #420, & Brick Red #900.

FOR INDUSTRIAL USE ONLY

KEEP AWAY FROM CHILDREN

For more information please contact:

Epoxy.com.

352-489-1666 (Phone)

352-465-3497 (Fax)

info@epoxy.com

www.epoxy.com

Epoxy.com a division of Epoxy Systems, Inc. warrants its products (when properly stored) for the period of time as follows: Epoxies, Product #315, Product #315BC, and Product #316 one (1) year; Polyesters, Methyl Methacrylates (normal) two (2) months and Polyurethanes Four (4) months; Power Tools and Equipment 90 days; Vinyl Esters, High Molecular Weight Methacrylates (HMMA) and all other resins (not specifically mentioned above) 30 days; hand tools (non-power tools) 30 days. Epoxy.com warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Epoxy.com. If any product fails to meet this warranty, the liability of Epoxy.com will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Epoxy.com within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). Epoxy.com may in its discretion refund the price received by Epoxy.com in lieu of replacing the material. No customer, distributor, or representative of Epoxy.com is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Epoxy.com. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Epoxy.com reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. Epoxy.com'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND Epoxy.com SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. All quotes and sales subject to availability.

CHEMICAL RESISTANCE			
REAGENT	Rating	REAGENT	Rating
Acetic Acid-5%	L	Iodine	R
Acetone	L	Lactic Acid-15%	R

Betadine	R	Methyl Ethyl Ketone	L
Bleach	L	Nitric Acid-10%	R
Citric Acid-30%	R	Skydrol	R
Crude Oil	R	Sodium Hydroxid-50%	R
Diesel Fuel	R	Sulfuric Acid-20%	R
Ethylene Glycol	R	Toluene	R
Faffy Acids	L	Urea	R
Gasoline	R	Vinegar	L
Hydrochloric Acid-15%	R	Xylene	R

R= Recommended for continuous Service L=Limited recommendation, occasional spills