

---

# EpoxySystems' Product #633

100% Solids Epoxy Novolac Coating

---

## DESCRIPTION

EpoxySystems' Product #633 is 100% solids epoxy novolac coating ideal for harsh chemical and solvent environments. EpoxySystems' Product #633 can be used as a seal coat for EpoxySystems' overlay systems, and where extreme chemical resistant performance is required. EpoxySystems' Product is used in secondary containment, solvent storage, pump pads, trenches, and other high exposure areas.

## ADVANTAGES

- Exhibits excellent resistance to strong acids, alkalis, and most industrial chemicals and solvents
- Can be applied in occupied facilities
- Can be applied in cool damp conditions
- Can be re-coated in 4 to 6 hours

## CONSIDERATIONS

- Concrete substrate must be free of dirt, waxes, curing agents, and other foreign materials.
- Steel surfaces must be free of grease and oils. Abrasive blast to SSPC-SP5.

## COMPOSITION

100% solids, modified amine adduct cured epoxy novolac resin.

## APPLICATION

### SURFACE PREPARATION

**Surface Preparation** is the most critical portion to any successful resinous system application. All substrates must be properly prepared as outlined in **Epoxy Systems TECHNICAL BULLETINS**. The **Epoxy Systems** tech service department is pleased to answer any questions.

### INSTALLATION

Will vary with application method.

Color	Light Grey or Brick Red		See Color Card.
		Gloss, 60°F	100

Solids Content	100%
Mix Ratio	2Ato 1B by volume
Pot Life	20 minutes @ 75°F
VOC	-0-

DRY TIME		
Foot Traffic	10 - 12	hours
Recoat	4 (min) -	12(max) hrs
Service	5 days	

PERFORMANCE PROPERTIES	
Tensile Strength ASTM D-638	10,400 psi
Adhesion to concrete ACI Committee 403	300 psi (100% concrete failure)
Hardness ASTM D-2240	86 Shore D
Abrasion Resistance ASTM C-501 (CS-17 Wheel)	30 mg loss
Service Temperature Mil-D-3134F	180-325 Degrees F. (Dry Heat)
Elongation	2.5%

## **CHEMICAL RESISTANCE**

**R-Recommended for intermittent immersion.**

**L- Limited recommendation, occasional spills**

REAGENT	RATING	REAGENT	RATING
Acetic Acid 20%	R	Urea	R
Acetone	L	Bleach	L
Methylene Chloride	R	Citric Acid	R
Crude Oil	R	Skydrol	R
Diesel Fuel	R	Sodium Hydroxide-50%	R
Ethylene Glycol	R	Sulfuric Acid-98%	R
Fatty Acids	R	Toluene	R
Gasoline	R	Lactic Acid	R
Methyl Ethyl Ketone	L	Nitric Acid 20%	R
Hydrochloric Acid- 36%	R	Xylene	L

## **WARRANTY**

Epoxy Systems, Inc. ("ESI") warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of ESI. If any product fails to meet this warranty, the liability of ESI will be limited to replacement of any non-conforming material if notice of such non-conformity is given to ESI within (1) one year of delivery of materials, ESI may in its discretion refund the price received by ESI in lieu of replacing the material. No customer, distributor, or representative of ESI is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of ESI. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. ESI reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. ESI'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND ESI SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

**This information is presented in good faith to assist in determining whether this product is suitable for application. No warranty or representation, however, is intended or made, nor is protection from any law or patent to be inferred, and all patent rights reserved.**

### **More information**

**For more information about this product or any other Epoxy Systems' product, please contact:**

### **Epoxy Systems, Inc.**

9370 SW 208<sup>TH</sup> CIR  
Dunnellon, FL 34431  
352-489-1666 (Voice)  
352-465-3497 (Fax)

[info@Epoxy.com](mailto:info@Epoxy.com) (E-Mail)  
[www.Epoxy.com](http://www.Epoxy.com) (WWW)

