# EpoxySystems' Product #715 Epoxy Delineator & Traffic Marker Adhesive

### **DESCRIPTION**

**PRODUCT #715 Delineator & Traffic Marker Adhesive** is a 2-component, 1:1 ratio, 100% solids, moisture insensitive epoxy resin system manufactured to bond delineators and traffic markers to median barriers, parapets, and roadways. **PRODUCT #715** will bond to steel, concrete, and asphalt. **PRODUCT #715** exceeds the requirements of AASHTO 237, Type 1 and the cured performance requirements of ASTM C881-87 Type I and IV, Grade 3, Class A, B & C.

#### **ADVANTAGES**

**PRODUCT #715** is in a convenient 1:1 ratio, for easy mixing and proportioning. One part of Product **#75** Filler may be added by volume for economy, when setting roadway traffic markers.

#### PHYSICAL PROPERTIES

Color "A" Component	White	
Color "B" Component	Black	
Color Mixed Material	Gray	
Consistency Mixed Material	Paste	
Gel Time Minimum - 60 grams (neat)	12 minutes at 75°F +/-2	
Bond Strength (psi) maximum ASTM C882	1 hour – 450	
$(@75^{\circ}F +/-)$	24 hours - 1800	
Shelf Life	1 year	
	Product #715	Georgia DOT
	Actual	Requirements
Pot Life	9 min.	6-11 min.
1 Hr. Bond	473 psi	180 psi
24 Hr. Bond	555 psi	400 psi
Property Retention	100%	90%

<sup>\*</sup> Gel Time and Bond Strength results comply with AASHTO M237 Type I.

# **PACKAGING**

PRODUCT #715 is available in 2 gallon and 10 gallon units.

## **COVERAGE**

When used neat, a 2-gallon unit of **PRODUCT #715** will cover approximately 100 square feet at a 30 mil thickness. When used as a mortar, a 2-gallon unit of **PRODUCT #715** mixed with 2 gallons by volume of **EpoxySystems' Product #75 Filler** will yield approximately 700 cubic inches of mortar.

#### **SURFACE PREPARATION**

For best results, areas to receive **PRODUCT #715** should be free of laitance, grease, oil, and any other contaminants, which would inhibit bond. Sandblasting, waterblasting, or wire-brushing for surface preparation are recommended

#### **MIXING**

Mix **PRODUCT #715** for approximately 3 minutes in a clean pail, using a slow speed drill and an **EpoxySystems' -Mixing Paddle**. To obtain a mortar, add **#75 Filler** slowly while continuing to mix. **PRODUCT #715** may be mixed with automatic dispensing equipment through a static mixer.

#### **LIMITATIONS**

**PRODUCT #715** should not be used when surface temperatures are below 35°F.

**CAUTION:** "A" Component contains epoxy resin. DANGER! "B" Component contains alkaline amines; strong sensitizer. May cause skin sensitization or other allergic responses. Use with good ventilation, particularly if material is heated or sprayed. Prevent all contact with skin or eyes. Wear protective clothing, goggles, gloves and/or barrier creams. Keep container closed when not in use. Wash thoroughly after handling.

**FIRST AID:** In case of skin contact, immediately wash with soap and water. in case of eye contact, flush eyes with copious amounts of water for at least fifteen (15) minutes. Remove contaminated clothing shoes. If irritation persists, seek medical attention. Wash clothing before reuse.

# FOR INDUSTRIAL USE ONLY KEEP AWAY FROM CHILDREN

For more information please contact:

Epoxy Systems, Inc. 352-489-1666 (Phone) 352-465-3497 (Fax) info@epoxy.com www.epoxy.com

Epoxy Systems™ Product Company ("ESI") warrants its products (when properly stored) for the period of time as follows one (1) year. ESI warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of ESI. If any product fails to meet this warranty, the liability of ESI will be limited to replacement of any nonconforming material if notice of such non-conformity is given to ESI within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). ESI may in its discretion refund the price received by ESI in lieu of replacing the material. No customer, distributor, or representative of ESI is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of ESI. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. ESI reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. ESI'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND ESI SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES. No returns on non-stocking colors, or items. No returns after 10 days. Returns must be unopened containers. All returns must be authorized in advance. Restocking charges will apply to returns. No returns on non-list priced items. All Returns are for merchandise (store) credit only, no cash or credit card credits. This information is presented in good faith to assist in determining whether this product is suitable for application. No warranty or representation, however, is intended or made, nor is protection from any law or patent to be inferred, and all patent rights reserved.