



Epoxy.com Product #11

100% Solids Epoxy Control Joint Filler

GENERAL DESCRIPTION

Product #11 is a 100% solids flexible epoxy joint filler for saw-cut joints of concrete slabs on grade, or to repair existing slabs. Product #11 absorbs the impact and shock of heavy loads and steel wheeled traffic, preventing erosion of control joint edges.

ADVANTAGES

- ➔ *High elongation*
- ➔ *Flexibility provides for joint movement*
- ➔ *Protects slabs edges from chipping*
- ➔ *Cures on damp or wet surfaces*
- ➔ *Field proven reliability*
- ➔ *Good shock absorption qualities*

SURFACE PREPARATION


Surface must be clean and sound. Remove all dirt, laitance, grease curing compounds and other foreign matter by sandblasting, or mechanical abrasion. Remove water and dust from all surfaces with an oil-free blast immediately prior to application.

MIXING INSTRUCTIONS

Temperature of Product #11 must be 50 degrees F or above at time of mixing. Stir each component separately before blending. Mix one part by weight of Part A with one part by weight of Part B for three minutes with a low speed electric drill motor equipped with a mixing paddle.

APPLICATION

For application on flat surfaces Product #11 can be poured. For vertical surfaces Product #11 can be thickened with Product #71. Contact Epoxy.com for more information on the thickening process. This mix of Product #11 & Product #71 can be applied by power or hand operated caulking gun, by trowel, or with a putty knife, or pumped from one of Epoxy.com' Binary Pumping Systems. In areas where cosmetics are important mask both sides of the substrate before applying the material.



LIMITATIONS

Use of **solvents** for thinning **will** prevent proper cure. Product #11 should not be installed on new concrete floors until maximum shrinkage has occurred. Generally speaking, this time period is a minimum of 28 days.

Safety Precautions

Prolonged or **repeated exposure may** cause eye and skin irritation. If contact occurs, **wash immediately and seek medical help. Use safety glasses with side shields** and wear protective rubber gloves.

Cleaning

All tools and equipment should be cleaned before the system gels. Use MEK, Acetone, or any lacquer solvent.

APPLICATION PROPERTIES @77 DEGREES F	
Mix Ratio	1:1 By Weight
Viscosity (mixed)	2,200 CPS
Gel Time	30 minutes
Consistency	Pourable liquid
Initial Cure	8 Hours (80% strength)
Final Cure	2-3 Days
Packaging (unit size)	1 gal., 5 gal.
Standard Colors	amber
Shore A. Hardness	70 to 80

PHYSICAL PROPERTIES	
Artificial Weathering (ASTM G23-75 Type D)	10-15% elastomeric property change after 1000 hours
Bond Cohesion after Water Immersion (Fed. Spec TT-S-00227E)	No Failure after 25% total movement
Tensile Strength (ASTM D-638)	600 p.s.i
Ultimate Elongation (ASTM D-638)	35%
Tear Resistance (ASTM D-624-73)	20 lb./in
Service Temperature	30 degrees F. to 180 Degrees F.

Coverage

Chart is based on the relationship between the 231 cubic inches in a US gallon and the dimensions of the joint. Coverage is per gallon

	¼	3/8	½	5/8	¾	1
¼	308	205	154	123	102	77
3/8		136	102	82	68	51
½			77	61	51	38
5/8				41	39	30
¾					34	25
7/8						22
1						19
Linear Feet Per Gallon						

**FOR INDUSTRIAL USE ONLY
KEEP AWAY FROM CHILDREN**

For more information please contact:

Epoxy.com.
352-489-1666 (Phone)
352-489-1625 (Fax)
info@epoxy.com
www.epoxy.com

Epoxy.com a division of Epoxy Systems, Inc. warrants its products (when properly stored) for the period of time as follows: Epoxies, Product #315, Product #315BC, and Product #316 one (1) year; Polyesters, Methyl Methacrylates (normal) two (2) months and Polyurethanes Four (4) months; Power Tools and Equipment 90 days; Vinyl Esters, High Molecular Weight Methacrylates (HMMA) and all other resins (not specifically mentioned above) 30 days; hand tools (non-power tools) 30 days. Epoxy.com warrants that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Epoxy.com. If any product fails to meet this warranty, the liability of Epoxy.com will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Epoxy.com within the warranty period for the material (as indicated above), or within 1 year of the delivery of materials (whichever is sooner). Epoxy.com may in its discretion refund the price received by Epoxy.com in lieu of replacing the material. No customer, distributor, or representative of Epoxy.com is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Epoxy.com. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Epoxy.com reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. Epoxy.com'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND Epoxy.com SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL

For the latest version of this document please see: www.epoxy.com/11.aspx