

- [Home](#) [Product Catalog](#) [About Us](#) [Adhesives](#) [Chemical Resistant](#) [Epoxy Coatings](#)
[Flooring](#) [Installation](#) [Joints](#) [Mortars & Grouts](#) [Primers & Sealers](#) [Specifier's Info](#)
[Structural](#) [Waterproofing](#) [MSDS & Tech Data](#) [Ordering Info](#)

The Right Product for the Right Job Since 1980



[\[Contact Us\]](#)

Epoxy Thickening Agent

For Thickening Epoxy and Other Resin Materials

Epoxy.com Product #71

Epoxy Thickening Agent Product #71 is a synthetic, amorphous, untreated fumed silicon dioxide. Because of its inert nature, it has been used in food such as ketchup as well as in shampoo and some cosmetics. When mixed into liquid resin, Epoxy Thickening Agent Product #71 functions as a resin thickener (flow control agent) and sometimes as an anti-settling, anti-caking agent. Its applications are many, including thickening, epoxy, polyester, and urethane. It is a versatile thickening agent that has even been used to "thicken" fresh water and sea water

Epoxy Thickening Agent Product #71 is an extremely fine particle size silica (silicon-dioxide / SiO₂). It is pure white and free-flowing. Each volume contains about 94% dead air space, with a density of only 2.3 lb/cu ft. On the other hand, water (density 62.4 lb / cu ft) weighs about 27 times more.

During the cure cycle, polyesters and epoxies being liquids tend to run off of vertical surfaces and accumulate on horizontal surfaces. The vertical surfaces become resin starved, whereas valleys become resin rich. The resin starved areas fail to achieve expected strength, and the resin rich areas suffer excessive shrinkage and warpage. Both of these undesirable conditions can be eliminated with the addition of the proper amount of Epoxy Thickening Agent Product #71. This thixotropic agent holds the liquid resin in place until the curing agent takes over and hardens it.

Normally, Epoxy Thickening Agent Product #71 is added at a 1% to 7% proportion based on the weight of the liquid (resin, hardener, thinner) involved. Because resin and Epoxy Thickening Agent Product #71 have such different densities, weight proportions are awkward. For example, one gallon of polyester weighs 9 pounds;

7% of 9 lbs is 10 ounces, which for Epoxy Thickening Agent Product #71 is about 1.25 gallons by volume.

For many situations, volumetric proportions are more convenient. A gallon of resin and a gallon of Epoxy Thickening Agent Product #71 is a 50/50 ratio by volume, but only 5% by weight. Incidentally, this 50/50 volume ratio results in a resin consistency about like vaseline. Lesser amounts yield a more liquid consistency, whereas greater amounts yield thicker pastes. The exact amount used is determined by the application. The addition of Epoxy Thickening Agent Product #71 has no effect on such properties as pot life, cure time, etc., and only affects strength to the degree that entrapped air reduced cross-sectional area.

For preciseness, a distinction has to be made between thickness and thixotropic. These terms are not the same. Thixotropic fluids are not always thick. They are only thick when they are left undisturbed. When they are being mixed or brushed, they appear to be fluid, but when left undisturbed for 20 to 30 seconds, they become thicker and stop flowing. This is how it is possible to have a liquid that is easy to brush, but will not run.

In order to get the maximum effect with the least amount of Epoxy Thickening Agent Product #71, the microscopic particles must be homogeneously dispersed throughout the resin. For best results, use a high shear mixing blade running at maximum speed. If a mixing stick must be used, expect to consume more of the agent. Whenever thixotropy is needed, no finer, more effective product exists than Epoxy.com Product #71 Epoxy Thickening Agent Product #71.

PROPERTIES:

Weight per Gallon: Approximately 8 oz.
pH (4% aqueous slurry): 3.7 - 4.3
B.E.T. Surface Area: 200 m² / g
325 mesh (44 microns) residue: 0.02% max
Bulk Density: 3.0 lb / cu ft (max)
Pour Density: 50 g/l Tap Density
Loss on Heating: <1.5% max
Loss on Ignition (@1000C): <2 wt%
Refractive Index: 1.46
X-ray form: Amorphous
Assay (Percent Silicon Dioxide): >99.8%
Oil Adsorption: 350 g / 100 g oil
Average Particle (Aggregate) Size: 0.2-0.3 microns

Proper mixing and installation is critical to the optimal success of all products. See [Installation Tips](#), [Techdata](#), & [MSDS](#) for more details on our products. Be sure to contact us with any questions and/or concerns that you have.

For more information please contact:

Epoxy.com

A Division of [Epoxy Systems, Inc](#)

A Vermont Corporation

USA

We have products that have passed the test of time as well as the best new [Systems](#) available today.

Since 1980 - 40 years of the highest quality products

Hours: 9AM-4PM Eastern Time (6AM-1PM Pacific Time)

Closed for lunch from 12Noon to 1PM

321-206-1833 Customer Service - Ordering and Order Status
Katey Lambert-Fontaine, VP - Chief Operations Officer
sales@epoxy.com

Technical Support
352-533-2167 Norm Lambert, President - Technical Support Director
info@epoxy.com

352-489-1666 Accounting and Administration
Debby Lambert, CEO, and CFO Debby Lambert, CEO, and CFO

352-489-1625 Fax line to all Departments

Copyright © 1994-2022 (**providing online information about the right product for the right job for over 25 years**) EPOXY.COM a division of Epoxy Systems, Inc. - Florida and Vermont. All rights reserved.



We accept MasterCard, Visa, American Express, Discover, or Wire Transfers.
>

[Home](#)

[Sales Terms](#)

[MSDS & Tech Data](#)

[Online Ordering Authorization Form](#)

[Add this page to Favorites](#)

[Secure Login](#)